

YIWU BABYSHOW MATERNAL CO.,LTD
NUMBER 718, THE WEST ROAD OF JIANGBIN, CHOUJIANG STREET, YIWU CITY, ZHEJIANG
PROVINCE, CHINA.

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A,B)reusable menstrual pads (Reusable menstrual pads, Out layer: waterproof PUL in blue, Middle: 2 layers microfiber, Inner: blue polar fleece)
(C)knitted fabric

Sample Color : (A)Blue;(B)Blue;(C)Blue

Composition : (A)Out layer: 100% polyester, Middle: 80% polyester + 20% nylon, Inner: 100% polyester;
(B)Out layer: 100% polyester, Middle: 80% polyester + 20% nylon, Inner: 100% polyester

Manufacturer : Yiwu Babyshow Maternal CO.,LTD

Sample Receiving Date : Nov 05, 2021

Testing Period : Nov 08, 2021 - Nov 11, 2021

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Hangzhou Branch

Jack Zhang

jack-yl_zhang(Account Executive)



SGS-CSTC Standards Technical Services Co., Ltd.
Hangzhou Branch Textile Laboratory.

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3-6F, No.4 Building, Huayue Hi-Tech Zone, No.1180, Bin'an Road, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571)86791199 f (86-571)87688901 www.sgs.com.cn
中国·浙江·杭州·滨江区滨安路1180号华业高科技产业园4号楼3-6层 邮编: 310052 t (86-571)86791199 f (86-571)87688901 e sgs.china@sgs.com

Test Result

Colour Fastness To Washing

(ISO 105-C06:2010; Test No.: A2S, Machine wash at 40°C with 4g/L ECE (B) and 1g/L Sodium Perborate with No Steel Balls.)

-	Unit	C
Change in Shade	Grade	4-5
Staining On Multi-fibre Stripe		
Acetate	Grade	4-5
Cotton	Grade	4-5
Polyamide	Grade	4-5
Polyester	Grade	4-5
Acrylic	Grade	4-5
Wool	Grade	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Dimensional Stability To Washing

(ISO 3759:2011/ISO 5077:2007/ISO 6330:2012; Using horizontal axis, front-loading type machine; Procedure No. Ref. 4H, Machine Wash At 30°C; with 2kg total dry mass (Type III (100% Polyester) Ballast+ specimen) and 'ECE(A)' detergent+ Sodium Perborate+ TAED, Line Dry.)

A	Original (cm)	After 1 Wash (cm)	After 1 Wash Shrinkage (%)
front length	31.0	30.7	-1.0
front width	11.7	11.6	-0.9
back length	31.0	30.7	-1.0
back width	11.7	11.5	-1.7

Remark: (+) Means Growth; (-) Means Shrinkage

Water Repellency (Spray Test)

(ISO 4920:2012; Spray Test - Tested under controlled condition, water temperature: 20±2°C)

C	No. 1	No. 2	No. 3
As Received			
Rating (No Unit)	3	3	3

Remarks: Nomenclature for rating:

- 100 (ISO 5) No sticking or wetting of the specimen face
- 90 (ISO 4) Slight random sticking or wetting of the specimen face
- 80 (ISO 3) Wetting of the specimen face at spray points
- 70 (ISO 2) Partial wetting of the specimen face beyond the spray points
- 50 (ISO 1) Complete wetting of the entire specimen face beyond the spray points
- 0 (ISO 0) Complete wetting of entire face




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC (Shanghai) Technical Services Co., Ltd.
Hangzhou Branch Laboratory

3-6F, No.4 Building, Huayue Hi-Tech Zone, No.1180, Bin'an Road, Binjiang District, Hangzhou, Zhejiang, China 310052 t (86-571)86791199 f (86-571)87688901 www.sgs.com.cn
中国·浙江·杭州·滨江区滨安路1180号华业高科技产业园4号楼3-6层 邮编: 310052 t (86-571)86791199 f (86-571)87688901 e sgs.china@sgs.com

Sample Photo



End of Report

